

R-2682-12

RTV silicone film adhesive

DESCRIPTION

- Two-part film adhesive
- Cures at room temperature or rapidly with heat

APPLICATION

- For bonding or sealing silicone elastomers and some metals or plastics
- For applications requiring shorter processing times, easy clean-up, and consistent bond thickness

PROPERTIES

Typical Properties	Average Result	Standard	NT-TM
Uncured:		·	·
Appearance, Part A	Translucent	-	139
Appearance, Part B	Translucent	ASTM D2090	002
Dimensional Analysis	0.012 inches (0.2 mm)	-	138
Application Life of Uncured Sheeting	4 hours Minimum		156
Cured: 4 hours at 65°C (149°F)			
Lap Shear Strength of Silicone Sheeting	100 psi Minimum	D1002	157

Properties tested on a lot-to-lot basis. Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications and testing parameters.



INSTRUCTIONS FOR USE

Apply the activator to one or both surfaces coming in contact with the film and allow the solvent to evaporate. Peel off the dark blue backing and apply the sheeting to one surface. Remove the other backing and apply the other surface to the film.

Substrate Considerations

Cures in contact with most materials, exceptions include: sulfurcured organic rubbers, latex, chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents.

Processing and Handling Recommendations

Product cures at a wide range of cure times and temperatures to accommodate different production needs.

<u>Contact</u> NuSil technical sales staff regarding questions or concerns related to a particular application

OPERATING TEMPERATURE

The operating temperature range of a silicone in any application is dependent on many variables, including but not limited to: temperature, time of exposure, type of atmosphere, exposure of the material's surface to the atmosphere, and mechanical stress. In addition, a material's physical properties will vary at both the high and low end of the operating temperature range. Silicone typically remains flexible at extremely low temperatures and has been known to perform at -50°C (-58°F) as well as resist breakdown at elevated temperatures up to 250°C (482°F). The user is responsible to verify performance of a material in a specific application.

ROHS AND REACH COMPLIANCE

Please <u>contact</u> NuSil Technology's Regulatory Compliance department with any questions or for further assistance.

SPECIFICATIONS

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please <u>contact</u> NuSil Technology for assistance and recommendations in establishing particular specifications.

WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 12 months from the date of

Packaging

12"x 12" Sheet Kit (30.48 x 30.48 cm) 14" x 20' Roll Kit (35.56 x 609.6 cm) Warranty

12 Months

shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

WARNINGS ABOUT PRODUCT SAFETY

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and contact NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain



available product safety information and take the necessary steps to ensure safety of use.

PATENT / INTELLECTUAL PROPERTY WARNING

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international

patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.



Silicone Sales & Services UK - Ireland - Benelux

© 2019 - Polymer Systems Technology Limited™ Unit 2. Network 4. Cressex Business Park, Lincoln Road, High Wycombe, Bucks. HP12 3RF

tel: +44 (0) 1494 446610

web: https://www.silicone-polymers.com

email: sales@silicone-polymers.co.uk

