


# Polymer Systems Technology Limited

UK & Ireland Distributor



© 2011 - Polymer Systems Technology Limited <sup>TM</sup>  
Unit 2. Network 4. Cressex Business Park,  
Lincoln Road, High Wycombe, Bucks. HP12 3RF  
Phone +44 (0) 1494 446610  
Fax: +44 (0) 1494 528611  
Web: <http://www.siliconepolymers.co.uk>  
Email: [sales@silicone-polymers.co.uk](mailto:sales@silicone-polymers.co.uk)



# MED-2000

Silicone Adhesive

NuSil Technology LLC  
1050 Cindy Lane • Carpinteria, CA 93013  
805/684-8780 • 805/566-9905 Fax  
www.nusil.com • silicone@nusil.com

An ISO 9001  
Certified Company

## Description

- One-part, solvent-free silicone
- Cure at room temperature upon exposure to atmospheric moisture

## Applications

- For bonding silicone elastomers to each other and some synthetics and metals

Properties	Average Result	ASTM	NT-TM
<b>Uncured:</b>			
Appearance	Translucent	D2090	002
Volatility (Cure Loss)	2.2%	D2288	004
Flow Rate (0.375 inch plunge for 1 minute)	2 inches (50.8 mm)	D2202	019
Tack-Free Time	10 minutes	C679	005
<b>Cured: 72 hours minimum @ ambient temp. and humidity</b>			
Specific Gravity	1.08	D792	003
Durometer, Type A	25	D2240	006
Tensile Strength	1,300 psi (9.0 MPa)	D412	007
Elongation	775%	D412	007
Tear Strength	75 ppi (13.2 kN/m)	D624	009
Stress @ 200% Strain	105 psi (0.72 MPa)	D412	007

Properties tested on a lot-to-lot basis. Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

## Instructions for Use

Apply MED-2000, supplied in cartridges, with the use of an appropriate caulking gun. Do not store alcohol near the worksite as traces of alcohol inhibit the catalytic system of the adhesive.

## Surface Preparation

Thoroughly clean surfaces being bonded or built-up with silicone adhesive using a non-oily cleaner or mild soap to remove any surface contaminants. Do not use synthetic detergents or oil-based soaps, as they may be absorbed and subsequently leach out. Rinse copiously with hot water and follow with a thorough rinse using distilled water. Use compatible degreasers to clean metal surfaces.

## Bonding Applications

Spread a layer of silicone adhesive on one of the surfaces. Squeeze both surfaces together to bond. Apply sufficient pressure to ensure full contact without forcing the silicone adhesive from between the pieces.

## Curing Time

Curing or vulcanization time depends upon the thickness of the silicone adhesive layer, relative humidity, and accessibility of atmospheric moisture to the curing adhesive. For sections of typical thickness, a relative humidity level between 20-60% is recommended to cure the adhesive at room temperature.

Generally the adhesive forms a thin, tack-free outer skin for thick section films within a few minutes after application. The vulcanization rate slows when exposing very thin films to excessive humidity ( $\geq 80\%$  relative air humidity). For films below 80 microns, the relative air humidity should be within 30% - 50%.

## Packaging

8 Gram Tube  
2 Ounce Tube (59 mL)  
5 Ounce Tube (148 mL)  
6 Ounce Tube (177 mL)

## Warranty

12 Months

Because MED-2000 cures upon exposure to moisture vapor, keep the tubes tightly closed when not in use. A plug of cured material may form in the tip of the tube. Remove or dispense the plug from the tube before using.

### **Non-Sterile Packaged Units**

The acidic nature of MED-2000 provides a natural bactericidal effect. While containers may be relatively free of microorganisms, it cannot be considered sterile unless subjected to a validated sterilization process. When the adhesive is fully cured it can withstand sterilization with ethylene oxide, dry heat, or steam autoclaving. The size and shape of fabricated articles must be considered when establishing the conditions of sterilization. Larger quantities and larger parts may require longer periods of heating and may retain ethylene oxide longer than small parts. It is the user's responsibility to determine the outgassing time required for a particular application if ethylene oxide sterilization methods are used.

### **Caution**

Do not use MED-2000 in the uncured state to repair or encapsulate living tissue in the body because approximately 4.5% acetic acid (vinegar-like odor) evolves in vapor form during the cure process. Avoid contact with eyes and skin, as uncured adhesive irritates. Take appropriate precautions if wearing contact lens. In case of contact, flush eyes with water, use a dry towel to remove from skin and contact a physician. Keep out of the reach of children.

### **FDA Master File**

A Master File for MED-2000 has been filed with the U.S. Food and Drug Administration. Customers interested in authorization to reference the Master File must contact NuSil Technology.

### **Specifications**

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology for assistance and recommendations in establishing particular specifications.

### **Warranty Information**

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

### **Warnings About Product Safety**

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and contact NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

## **Patent / Intellectual Property Warning**

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.