

CV-2680-12

Controlled volatility film adhesive

DESCRIPTION

- Two-part film adhesive
- Cures at room temperature or rapidly with heat

Meets or exceeds the ASTM E 595 low outgas specifications outlined in NASA SP-R-0022A and European Space Agency PSS-014-702, with a TML of $\leq 1\%$ and CVCM of $\leq 0.1\%$

APPLICATION

- For electronic and space applications requiring low outgassing and minimal volatile condensables to avoid condensation in sensitive devices
- For bonding or sealing silicone elastomers and some metals or plastics
- For applications requiring shorter work times, easy clean-up, and consistent bond thickness

PROPERTIES

Typical Properties	Average Result	Standard	NT-TM
Uncured:			
Appearance, Part A	Translucent	-	139
Appearance, Part B	Translucent	ASTM D2090	002
Dimensional Analysis	0.013 inches (0.3 mm)	-	138
Cured: 4 hours at 65°C (149°F)			
Lap Shear Strength	250 psi (1.7 MPa)	ASTM D1002	157
Coefficient of Linear Thermal Expansion			
-25 to 250°C	465 ($\mu\text{m}/(\text{m}^\circ\text{C})$)	ASTM D3386	-
Collected Volatile Condensable Material (CVCM)	0.06%	ASTM E595	072
Total Mass Loss (TML)	0.29%	ASTM E595	072
Base Properties (material not in Film form):			
Tensile Strength	1,450 psi (10.0 MPa)	ASTM D412	007
Elongation	850%	ASTM D412	007
Tear Strength	115 ppi (20.3 kN/m)	ASTM D624	009
Young's Modulus	315 psi (2.2 MPa)	-	-
Lap Shear Strength (primed w/ SP-270)	250 psi (1.7 MPa)	ASTM D1002	010

Typical Properties	Average Result	Standard	NT-TM
After High Temperature Exposure: 7 days @ 240°C (464°F)			
Tensile Strength	420 psi (2.9 MPa)	ASTM D412	007
Elongation	395%	ASTM D412	007
Tear Strength	50 ppi (8.6 kN/m)	ASTM D624	009
Young's Modulus	150 psi (1.0 MPa)	-	-
Lap Shear Strength (primed w/ SP-270)	200 psi (1.4 MPa)	ASTM D1002	010
10 cycles of 5 minutes at 300°C (572°F)			
Tensile Strength	1,400 psi (9.5 MPa)	ASTM D412	007
Elongation	750%	ASTM D412	007
Tear Strength	110 ppi (19.2 kN/m)	ASTM D624	009
Young's Modulus	300 psi (2.1 MPa)	-	-
Lap Shear Strength (primed w/ SP-270)	300 psi (2.1 MPa)	ASTM D1002	010

The test data shown for this material is the average value for typical properties. All of these properties may not be tested on a lot to lot basis and cannot be used to draft specifications. Please [contact](#) NuSil® for assistance and recommendations in establishing limits for product specifications.

INSTRUCTIONS FOR USE

Apply the activator to one or both surfaces coming in contact with the film and allow the solvent to evaporate. Peel off the dark blue backing and apply the sheeting to one surface. Remove the other backing and apply the other surface to the film.

Substrate Considerations

Cures in contact with most materials, exceptions include: sulfur-cured organic rubbers, latex, chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents.

Processing and Handling Recommendations

Product cures at a wide range of cure times and temperatures to accommodate different production needs. [Contact](#) NuSil technical sales staff regarding questions or concerns related to a particular application.

OPERATING TEMPERATURE

The operating temperature range of a silicone in any application is dependent on many variables, including but not

Packaging

12"x 12" Sheet Kit (0.011 kg)
(30.48 x 30.48 cm)
14" x 20' Roll (0.925 kg)
(35.56 x 609.6 cm)

Warranty

12 Months

limited to: temperature, time of exposure, type of atmosphere, exposure of the material's surface to the atmosphere, and mechanical stress. In addition, a material's physical properties will vary at both the high and low end of the operating temperature range. Silicone typically remains flexible at extremely low temperatures and has been known to perform at -50°C (-58°F) as well as resist breakdown at elevated temperatures up to 250°C (482°F). The user is responsible to verify performance of a material in a specific application.

ROHS AND REACH COMPLIANCE

Please [contact](#) NuSil's Regulatory Compliance department with any questions or for further assistance

SPECIFICATIONS

Do not use the typical properties shown in this technical profile as a basis for preparing specifications. Please [contact](#) NuSil for assistance and recommendations in establishing limits for product specifications.

WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil provides a specific written warranty of fitness for a particular use, NuSil's sole warranty is that the product will meet NuSil's then current specification. NuSil specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil expressly disclaims any liability for incidental or consequential damages.

WARNINGS ABOUT PRODUCT SAFETY

NuSil believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any

application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil makes no warranty concerning fitness for any use or purpose. NuSil has completed no testing to establish safety of use in any medical application.

NuSil has tested this material only to determine if the product meets the applicable specifications. (Please [contact](#) NuSil for assistance and recommendations when establishing specifications.) When considering the use of NuSil products in a particular application, review the latest Material Safety Data Sheet and [contact](#) NuSil with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

PATENT / INTELLECTUAL PROPERTY WARNING

NuSil disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.



Polymer Systems Technology Limited

Silicone Sales & Services UK - Ireland - Benelux

© 2022 - **Polymer Systems Technology Limited™**
Unit 2. Network 4. Cressex Business Park,
Lincoln Road, High Wycombe, Bucks. HP12 3RF

tel: +44 (0) 1494 446610

web: <https://www.silicone-polymers.com>

email: sales@silicone-polymers.co.uk

