

CV7-1142-1

Non-corrosive controlled volatility RTV silicone adhesive/sealant

DESCRIPTION

- One-Part, white, non-slumping RTV silicone

Meets or exceeds the ASTM E 595 low outgas specifications outlined in NASA SP-R-0022A and European Space Agency PSS-014-702, with a TML of \leq 1% and CVCM of \leq 0.1%

APPLICATION

- For applications requiring low outgassing and minimal volatile condensables under extreme operating conditions
- As a sealing, caulking, adhesive or potting material in electrical and space applications to provide protection of sensitive circuits including in connectors, switches and electrical components
- For sealing openings in modules or housings where grooves or other configurations require a non-flowable to limited flow material
- For applications requiring a broader operating temperature range

PROPERTIES

Typical Properties	Average Result	Standard	NT-TM
Uncured:			
Appearance*	White	ASTM D2090	002
Tack-Free Time*	20 minutes	ASTM C679	005
Flow*	0.7 inches (1.8 cm)	ASTM D2202	019
Extrusion Rate* (Performed using a SEMCO 440 nozzle with a 1/8" orifice and 90 +/- 5 psi air pressure)	20 g/min	ASTM C603	033
Cured: 7 days minimum at ambient temperature and humidity	/		
Appearance*	White, Elastomer	ASTM D2090	002
Specific Gravity*	1.13	ASTM D792	003
Durometer, Type A*	40	ASTM D412	007
Tensile Strength*	700 psi (4.8 MPa)	ASTM D412	007
Elongation	300% Version uploaded 29/05/2022	ASTM D412	007
	· · · · · · · · · · · · · · · · · · ·		





Typical Properties	Average Result	Standard	NT-TM
Tear Strength*	60 ppi (10.6 kN/m)	ASTM D624	009
Coefficient of Linear Thermal Expansion			
Below Tg (-150°C to -115°C)	90 ppm/°C (90 μm/m/°C)	ASTM D3386	-
Above Tg (-95°C to 250°C)	320 ppm/°C (320 μm/m/°C)	ASTM D3386	-
Dielectric Strength	1,180 volts/mil (46.5 kV/mm)	ASTM D149	-
Collected Volatile Condensable Material (CVCM)*	0.04%	ASTM E595	072
Total Mass Loss (TML)*	0.39%	ASTM E595	072

*The test data shown for this material is the average value for typical properties. All of these properties may not be tested on a lot to lot basis and cannot be used to draft specifications. Please <u>contact</u> NuSil[®] for assistance and recommendations in establishing limits for product specifications.

INSTRUCTIONS FOR USE

Apply CV7-1142-1, supplied in cartridges, with the use of an appropriate caulking gun.

Inhibition Concerns

Although generally considered to be non-corrosive to most substrates, the oxime cure system may cause discoloration in the presence of copper or copper alloys.

HEAT AND LOW-TEMPERATURE RESISTANCE

The operating temperature range of a silicone in any application is dependent on many variables, including but not limited to: temperature, time of exposure, type of atmosphere, exposure of the material's surface to the atmosphere, and mechanical stress. In addition, a material's physical properties will vary at both the high and low end of the operating temperature range. This type of silicone typically remains flexible at extremely low temperatures and has been known to perform at -120°C (-248°F) as well as resist breakdown at elevated temperatures up to 300°C (572°F). The user is responsible to verify performance of a material in a specific application.

ROHS AND REACH COMPLIANCE

Please <u>contact</u> NuSil's Regulatory Compliance department with any questions or for further assistance

PackagingWarranty6 Ounce Tube (0.168 kg)12 Months

SPECIFICATIONS

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please <u>contact</u> NuSil for assistance and recommendations in establishing limits for product specifications.

WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil provides a specific written warranty of fitness for a particular use, NuSil's sole warranty is that the product will meet NuSil's then current specification. NuSil specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil expressly disclaims any liability for incidental or consequential damages.





WARNINGS ABOUT PRODUCT SAFETY

NuSil believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil makes no warranty concerning fitness for any use or purpose. NuSil has completed no testing to establish safety of use in any medical application.

NuSil has tested this material only to determine if the product meets the applicable specifications. (Please <u>contact</u> NuSil for assistance and recommendations when establishing specifications.) When considering the use of NuSil products in a particular application, review the latest Material Safety Data Sheet and <u>contact</u> NuSil with any questions about product safety information. Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

PATENT / INTELLECTUAL PROPERTY WARNING

NuSil disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.



Silicone Sales & Services UK - Ireland - Benelux

© 2022 - Polymer Systems Technology Limited™ Unit 2. Network 4. Cressex Business Park, Lincoln Road, High Wycombe, Bucks. HP12 3RF

tel: +44 (0) 1494 446610

web: https://www.silicone-polymers.com

email: sales@silicone-polymers.co.uk

