

EPM-2421

Low volatility silicone elastomer

DESCRIPTION

- Two-part, clear silicone system
- Offers low modulus and low viscosity
- 1:1 Mix Ratio (Part A: Part B)

APPLICATION

- For applications requiring low volatility and high purity
- Designed for protection of electrical components and assemblies against shock, vibration, moisture, dust, chemicals, and other environmental hazards
- Ideal for applications in which clarity and low viscosity are important

PROPERTIES

Typical Properties	Average Result	Standard	NT-TM
Uncured:			
Appearance	Transparent	ASTM D2090	002
Viscosity, Part A	3,750 cP (3,750 mPas)	ASTM D1084, D2196	001
Viscosity, Part B	2,700 cP (2,700 mPas)	ASTM D1084, D2196	001
Work Time	3 hours	-	008
Tack-Free Time	5 hours	ASTM C679	005
Cured: 15 minutes at 150°C (302°F)			
Specific Gravity	1.02	ASTM D792	003
Durometer, Type A	50	ASTM D2240	006
Tensile Strength	850 psi (5.9 MPa)	ASTM D412	007
Elongation	90%	ASTM D412	007
Lap Shear Strength primed with CF1-135	250 psi (1.73 MPa)	ASTM D1002	010
Volatile Content (1 hour at 275°C)*	0.7%	ASTM D2288	004
Volume Resistivity*	8.5 X 10 exp ¹⁴	ASTM D257	153
Dielectric Strength*	610 V/mil (24.0 kV/mm)	ASTM D149	-
Dielectric Constant, 100 Hz*	2.8	ASTM D150, D924	906

Typical Properties	Average Result	Standard	NT-TM
Dielectric Constant, 1 kHz*	2.8	ASTM D150, D924	906
Loss Tangent, 100 Hz*	0.0003	ASTM D150, D924	906
Loss Tangent, 1 kHz*	0.0004	ASTM D150, D924	906
Coefficient of Linear Expansion (-150°C to -170°C)*	87 µm/(m°C)	ASTM E831	-
Coefficient of Linear Expansion (-70°C to 200°C)*	297 µm/(m°C)	ASTM E831	-
Glass Transition Temperature (Tg)*	-116°C (-176.8°F)	ASTM D3418	-
Ionic Content, Na *	<6 ppm	MIL-STD-883	-
Ionic Content, K *	<3 ppm	MIL-STD-883	-
Ionic Content, Cl *	<6 ppm	MIL-STD-883	-

*The above properties NOT are tested on a lot-to-lot basis. Do not use as a basis for preparing specifications. Please [contact](#) NuSil Technology for assistance and recommendations in establishing particular specifications

INSTRUCTIONS FOR USE

Mixing and Vacuum Deaeration

Combine Part A and Part B in a 1:1 mix ratio prior to use. Airless mixing, metering or dispensing equipment is recommended for production operations. If mixing by hand, take care to minimize air entrapment.

Remove air entrapped during mixing by common vacuum deaeration procedure, observing all applicable safety precautions. Slowly apply full vacuum to a suitable container of at least four times the volume of material being de-aired. Hold vacuum until bulk deaeration is complete. For further information please see [Mixing and De airing Addition Cure Silicones](#).

Substrate Considerations

EPM-2421 cures in contact with most materials common to electronic assemblies. Exceptions include butyl and chlorinated rubbers, some Tin condensation cure silicones and unreacted residues of some curing agents. Units being encapsulated or potted should be clean and free of surface contaminants. Containers and dispensers being used should also be clean and dry. Cure inhibition can usually be prevented by washing all containers with solvent or volatizing the contaminant by heating. For further information please see [Avoiding Cure Inhibition](#).

Note: Some bonding application may require the use of a primer. NuSil Technology's CF1-135 silicone primer is recommended. For further information please see [Choosing a Silicone Primer / Adhesive System for Engineering Applications](#).

Packaging

50 mL Side-by-Side Kit
 50 Gram Kit
 100 Gram Kit
 400 mL Side-by-Side Kit
 500 Gram Kit

Warranty

12 Months

ROHS AND REACH COMPLIANCE

Please [contact](#) NuSil Technology's Regulatory Compliance department with any questions or for further assistance

SPECIFICATIONS

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please [contact](#) NuSil Technology for assistance and recommendations in establishing particular specifications.

WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 12 months from the date of

shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

WARNINGS ABOUT PRODUCT SAFETY

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please [contact](#) NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the latest Material Safety Data Sheet and [contact](#) NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

PATENT / INTELLECTUAL PROPERTY WARNING

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.



Polymer Systems
Technology Limited

Silicone Sales & Services UK - Ireland - Benelux

© 2019 - Polymer Systems Technology Limited™
Unit 2. Network 4. Cressex Business Park,
Lincoln Road, High Wycombe, Bucks. HP12 3RF

tel: +44 (0) 1494 446610

web: <https://www.silicone-polymers.com>

email: sales@silicone-polymers.co.uk

