

# R-2100-2

## Black silicone coating / marking ink

### DESCRIPTION

- Two-part, addition-cure black silicone ink dispersed in xylene
- Cures rapidly with heat

### APPLICATION

- For use as a marking ink for silicone rubber parts and other components
- Use in applications requiring a rapid cure
- Various application methods including pad printing and screen printing

### PROPERTIES

Typical Properties	Average Result	Metric Conv.	Standard	NT-TM
<b>Uncured:</b>				
Appearance	Black	-	ASTM D2090	002
Viscosity, Part A	800 cP	800 mPa.s	ASTM D1084, D2196	001
Viscosity, Part B	2,850 cP	2,850 mPa.s	ASTM D1084, D2196	001
Non-Volatile Content	60%	-	ASTM D2288	004
Recommended Cure Schedule	5 minutes at 302°F	5 minutes at 150°C	-	-

The test data shown for this material is the average value for typical properties. All of these properties may not be tested on a lot to lot basis and cannot be used to draft specifications. Please [contact](#) NuSil® for assistance and recommendations in establishing limits for product specifications.

## INSTRUCTIONS FOR USE

### Mixing

Thoroughly stir individual components prior to addition to ensure homogeneity. Mix in a 1:1 ratio by weight or volume. Exercise care to prevent solvent loss during deairing. Accomplish additional dilution for thin film applications by adding appropriate solvent.

Warning: Consult the MSDS for R-2100-2 prior to use as its solvent carrier is hazardous.

### Substrate Considerations

R-2100-2 will cure in contact with most materials common to electrical and electronic assemblies. Exceptions include sulfur-cured organic rubbers, latex, chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents.

### Warnings About Product Safety

NuSil believes the information and the data contained herein are accurate and reliable. However, the user is responsible to determine the material's suitability and safety of use. NuSil cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil makes no warranty concerning fitness for any use or purpose.

NuSil has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil for assistance and recommendations when establishing specifications.) When considering the use of NuSil products in a particular application, review the latest Material Safety Data Sheet and contact NuSil with any questions about product safety information.

## SPECIFICATIONS

Do not use the typical properties shown in this technical profile as a basis for preparing specifications. Please [contact](#) NuSil for assistance and recommendations in establishing limits for product specifications.

## WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC is 6 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil provides a specific written warranty of fitness for a particular use, NuSil's sole warranty is that the product will meet NuSil's then current

### Packaging

2 Pint Kit (0.91 kg)  
2 Gallon Kit (7.28 kg)

### Warranty

6 Months

specification. NuSil specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil expressly disclaims any liability for incidental or consequential damages.

## WARNINGS ABOUT PRODUCT SAFETY

NuSil believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil makes no warranty concerning fitness for any use or purpose. NuSil has completed no testing to establish safety of use in any medical application.

NuSil has tested this material only to determine if the product meets the applicable specifications. (Please [contact](#) NuSil for assistance and recommendations when establishing specifications.) When considering the use of NuSil products in a particular application, review the latest Material Safety Data Sheet and [contact](#) NuSil with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

## PATENT / INTELLECTUAL PROPERTY WARNING

NuSil disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil does not warrant the use or sale of the

products described herein will not infringe the claims of any domestic or international patent/intellectual property right

covering the product itself, its use in combination with other products, or its use in the operation of any process.



**Polymer Systems**  
Technology Limited

## Silicone Sales & Services UK - Ireland - Benelux

© 2022 - Polymer Systems Technology Limited™  
Unit 2. Network 4. Cressex Business Park,  
Lincoln Road, High Wycombe, Bucks. HP12 3RF

tel: +44 (0) 1494 446610

web: <https://www.silicone-polymers.com>

email: [sales@silicone-polymers.co.uk](mailto:sales@silicone-polymers.co.uk)

